

Due to the technical digital cameras and inconsistencies of display monitors, the characteristics and colors of the fabrics seen on your screen may be slightly different than the actual

T18FVS026 Flat Black

TEXTILENE® nano™ 95 is a durable, yet lightweight synthetic fabric. It is lighter and finer with the same technical qualities as the original TEXTILENE®. TEXTILENE® nano™95 is excellent for exterior and interior use and can reduce energy costs while blocking up to 95% of the sun's harmful rays.

*Custom colors and widths available. Minimum order of 1000 yds. Upcharges may apply. ** Available in 28 lyd rolls.

Specifications

Jan 2020

REACH Compliant - Regulated by Registration, Evaluation, Authorization and Restriction of Chemicals. REACH places greater responsibility on industry to manage the risks that chemicals may pose to human health and the environment.





Environmental Certification - GREENGUARD gold certified. Acceptable for use in environments such as schools and healthcare facilities. Complies with requirements of the State of California's Department of Public Health "Standard Method for Testing and Evaluation of Volatile Organic Chemical Emissions from Indoor Sources Using Environmental Chambers, Version 1.1 (2010)" (also known as California Section 01350).

RoHS Compliant - Free of Lead (Pb), Cadmium (Cd), Mercury (Hg), Hexavalent chromium (Hex-Cr), Polybrominated biphenyls (PBB), and Polybrominated diphenyl ethers (PBDE).

Bacteria and Fungal Resistance - Passes ASTM E 2180, ASTM G21. Includes specially formulated antimicrobial.



FLAME RESISTANT

















Technical Data


Item Number: T18FVS, T18FVT


Product Description: A woven fabric using .014" diameter vinyl coated 420 denier polyester core yarns woven in the warp and fill.

Attribute	ASTM	Warp	Fill	Typical		
Construction, end/inch	D3775-17	36.0 ±0.5	34.0 ±0.5			
Weight, oz/yd²	D3776-09			14.7		
Weight, g/m ²	D3776-09			498.5		
Tensile Strength (grab), lbf / daN	D5034-09	423.6/ 192.1	382.2/ 173.4			
Tensile Strength (strip), lbf / daN	D5035-11	218.5 / 99.1	188.4 / 85.5			
Tear Strength (trapezoidal), lbf / daN	D1117-99	58.4 / 26.5	42.2 / 19.1			
Elongation, %	D5035-11	12.7	11.6			
Abrasion Resistance (CS10/500 cycles/ with no added weight)	D3884-09	No Exposure of Core Yarn				
Flammability Rating		CA Title 19 & NFPA 701				
Weatherability, 1200 hours	G154-16	No Discoloration				
Mildew Resistance	G21-13	Pass				
Thickness, inches/mm	D1777-15	0.026 / 0.66				
The above results are a r Present		of real data from on is incorporate		oles.		

Fenestration Properties for Twitchell Shade Material Exterior Use **45 Degree Profile Angle**

	Total Solar			Visible		Insulating Glass			
Description	Ts	Rs	As	Tv	Rv	Av	1/2" Clr.	1" Clr.	1" HA
Black	5	8	87	6	9	85	0.11	0.11	0.11





DISTRIBUTED OR MANUFACTURED BY:

East Facing Window









Due to the technical limitations of digital cameras and inconsistencies of display monitors, the characteristics and colors of the fabrics seen on your screen may be slightly different than the actual product.

T18FVS026 Flat Black